

DINITROL® Sealant

Underbody Protection

Characteristics:

- Brown bronze coloured
- Temperature resistant
- Low temperature flexible
- Stone chip resistance
- Excellent corrosion protection
- Enduring

Applications:

DINITROL Sealant is an underbody product for treatment of vehicles during production, at import plants and in the aftermarket. When applied to a clean, dry surface, it adheres to both painted surfaces and those coated with a layer of PVC or similar material. Zinc, rubber and plastics are completely unharmed by the product. A clean and economic treatment on the line is assured by easy application and high solid content. DINITROL Sealant is also designed to be used on spare parts, machines and iron and steel structures in highly corrosive environment.

DINITROL Sealant is also very suitable as a transport and storage anti-corrosive for long-term transporting or warehousing under extreme corrosive circumstances.

Method of use:

DINITROL Sealant can be applied by manual or automatic application equipment, airless.

Technical properties:

Colour:	Brown
Type of film:	Hard, waxy
Density at 23°C:	1040 kg/m ³
Viscosity at 23°C:	800 mPas
Dry matter content:	62% by weight
Flash point:	41°C
Aromatic content in solvent:	< 0,5%
Rec film thickness:	300 – 500 µm
Drying time:	6 – 12 h
Low temperature adhesion:	- 20°C
Removability:	White Spirit
Heat resistance:	> 130°C
Salt spray test:	1500 h
Application temperature:	15 – 30°C

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com