

DINITROL® 2000 A

Underbody Protection

Characteristics:

- Brown bronze
- Aftermarket applications
- Dual application with several thin coatings
- Easy applied
- Long term endurance
- Good abrasion resistance

Applications:

DINITROL 2000 A is primarily designed as an under-body corrosion preventative for vehicles such as cars, trucks and buses, during production, at import plants and aftermarket. A clean and economical treatment is assured by the easy application of the product. The film is also heat resistant and maintains its flexibility also at low temperatures. The product gives an excellent corrosion protection in thin as well as in thick films.

Method of use:

DINITROL 2000 A can be applied by high pressure manual or automatic spray equipment. Its properties contribute to a particularly clean working environment due to its thixotropic nature which prevents dripping and running.

Technical properties:

Colour:	Black
Type of film:	Elastic, waxy
Density at 23°C:	1040 kg/m ³
Viscosity at 23°C:	870 mPa s
Dry matter content:	62% by weight
Flash point:	40°C
Aromatic content in solvent:	< 0.5%
Rec film thickness:	300 – 500 µm
Drying time:	10 – 24 hrs
Effetc on car paint:	None
Low temperature adhesion:	- 30°C
Heat resistance:	> 130°C
Salt spray test 300 µm DFT:	2000 hrs
Available in:	60 L Drum / 208 L Drum / Container

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com