

## DINITROL 25 B

Universal Protection

### Characteristics:

- Transparent
- Extremely penetrating
- Oily, easy removable film
- Short and medium term storage indoor or outdoor under cover

### Applications:

DINITROL 25 B is designed to protect metallic parts in the interim between different production operations and during limited periods of storage, in particular when the parts are wetted by e.g. rinsing water, cutting oil emulsions etc. DINITROL 25 B provides excellent corrosion protection indoors at extremely low film thickness.

### Method of use:

DINITROL 25 B may be applied by dipping, brushing or spraying. Best results are achieved by dipping. To obtain quick and effective water repellence, it is recommended that the parts dipped in the bath are agitated or disturbed to ensure maximum coverage. Spraying may be undertaken by using either airless or airmix type of equipment.

### Technical properties:

Colour:	transparent
Type of film:	greasy
Density at 23°C:	820 kg/m <sup>3</sup>
Dry matter content:	25% by weight
Flash point:	> 62°C
Aromatic content in solvent:	< 0.5%
Recommended film thickness wet:	10 µm
Recommended layer thickness:	2 µm
Drying time:	30 mins.
Effect on car paint:	none
Low temperature adhesion:	- 40°C
Penetration:	> 100 mm
Available in:	20 l Pail / 208 l Drum / Container

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telefon:  
+49 (0) 52 81 / 9 82 98-0  
Telefax:  
+49 (0) 52 81 / 9 82 98-60  
E-Mail:  
service@dinol.com