

DINITROL 4015 Spray

Universal Protection

Characteristics:

- Brown / Red transparent
- Forming a hard, tack-free film.
- Extremely high corrosion resistance at low film weight
- Suitable for steel as well as white metals

Applications:

Super penetrating water displacing corrosion inhibiting compound, leaving a tack - free, brown transparent, firm film.

For protection of all, commonly used metals and alloys. Extremely good performance on light metals.

DINITROL 4015 Spray can be used in many situations, offering extremely good corrosion prevention at very low film weight.

The viscosity is adjusted to allow very easy and safe application also in difficult to reach-areas of the construction.

Since DINITROL 4015 Spray forms a firm film, movable parts should be masked before treatment, unless sufficient control of the spray is possible.

Method of use:

DINITROL 4015 Spray is best applied when spraying from a distance of 20 – 40 cm onto open surfaces. In cavities the application is best done by using a suitable extension hose, attached to the spray button.

Solvent such as aliphatic hydrocarbon can easily remove the film. For the assembly or control of the parts treated with DINITROL 4015 Spray, it is not necessary to remove the film.

Technical properties:

| | |
|------------------------|----------------------------------|
| Colour: | transparent brown / red |
| Type of film: | tack free |
| Density at 23°C: | 755 kg/m ³ |
| Dry matter content: | 34% by weight |
| Flash point: | < -20°C |
| Rec. film thickness: | 15 µm |
| Drying time: | 60 min tack-free |
| Penetration: | > 80 mm |
| Salt Spray Resistance: | > 1500 h at 15 microns DFT or Al |

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com