

DINITROL 9220

Stone chip Protection / Sound damping

Characteristics:

- Grey / Black
- Water borne
- Stone chip protection
- Sound damping
- Corrosion protection

Applications:

DINITROL 9220 is designed for sound damping applications on Buses, Trains, Commercial vehicles and Cars. It is used for underbody coating and stone chip protection. Specific use is the engine compartment and underbody of Buses as well as underbody and interior of trains. Other areas for use is sound deadening of aggregate buildings and metal constructions in vehicle-, railway- and shipbuilding, turbine housings, metal doors and air-condition plants.

Method of use:

DINITROL 9220 is applied at room temperature by airless spraying. The exact application parameters do depend on the pump, the nozzle, ambient temperature, etc. Tip blockages will be prevented by storing the tip in water directly after use. Further it is possible to apply DINITROL 9220 by spatula or brush.

Technical properties:

Colour:	grey / black
Flash Point:	not applicable
Non-Volatile Content:	75%
Recommended film thickness wet:	1700 µm
Viscosity Rheotec RC20 (23°C) DIN 114, Dmax=452s-1	1,3 Pa.s
Specific Gravity:	1,25 g/m ³
Sagging 3 mm wet film:	no sagging
Corrosion Resistance:	500 h Saltspray, no corrosion
Available in:	20 L Pail

For all relevant safety advices please read the material safety data sheet or the packaging label.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendation which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

DINOL GmbH
Pyrmonter Str. 76
D-32676 Lügde
Telefon:
+49 (0) 52 81 / 9 82 98-0
Telefax:
+49 (0) 52 81 / 9 82 98-60
E-Mail:
service@dinol.com